



MARPOL
EVA 28150
Ethylene Vinyl Acetate



PRODUCT DATA SHEET

PROPERTY	VALUE	ASTM
Melt Index (g/10min)	150	D 1238
Density (g/cm ³)	0.946	D 1505
Vinyl Acetate Content (wt %)	27.6	
Tensile Strength at Break (psi)	6300	D 638
Elongation at Break (%)	640	D 638
Flexural Modulus - 1 % Secant (psi)	1900	D 790
Durometer Hardness, Shore A	72	D 2240
Durometer Hardness, Shore D	16	D 2240

Recommended Applications

Adhesives, sealants, hot melt adhesives, industrial sealants and wax blends.

Description

MARPOL® EVA 28150 is a high flow Vinyl Acetate copolymer that has excellent compatibility with hydrocarbons, most waxes, and natural tackifiers. It is designed for making hot melt adhesives, sealants and wax blends.

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility.