




MARPOL
PSH 6073
High Impact Polystyrene



PRODUCT DATA SHEET

PROPERTY	VALUE	ASTM
Melt Index (g/10 min)	7.5	D 1238
Vicat Softening °C	100	D 1525
HDT (Unannealed) °C	77	D 648
Tensile Strength (MPa)	240	D 638
Elongation (%)	45	D 638
Flexural Strength (MPa)	450	D 790
Flexural Modulus (MPa)	22500	D 790
Izod Impact Notched (ft-lbs/in)	3	D 256

Processing: Molding

Applications: Suitable for home appliances, lamp shades, wall clocks, gift sets, picnic boxes, air coolers, and watch cases.

MARPOL® PSH 6073 can - in principle - be used in food contact applications in the USA (FDA) and in Canada (HBP). Migration or use limitations may apply.

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility.