



MARPOL
LDF 720
Low Density Polyethylene



PRODUCT DATA SHEET

PROPERTY		VALUE	ASTM
Melt Index		2.0	D 1238
Density (g/cm ³)		0.921	D 1505
Dart Drop Impact F50 (grams)		55-100	D 1709
Tensile Strength at Yield (psi)	MD TD	1500- 3400 1450- 1700	D 882
Elongation at Break (%)	MD TD	250 500- 750	D 882
1% Secant Modulus at Yield (psi)	MD TD	27000- 31000 31900- 35000	D 882
Haze (%)		6.5- 8.8	D 1003

Additives: No Slip, No Antiblock

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility.