



MARPOL

LL4F 802

Linear Low Density Polyethylene



PRODUCT DATA SHEET

PROPERTY		VALUE	ASTM
Melt Index 190°C/ 2.16kg (g/10 min)		2.0	D 1238
Density (g/cm ³)		0.919	D 1505
Dart Drop Impact, F50 (grams)		117	D 1709A
Tensile Strength at Yield (psi)	MD	1800	D 882
	TD	1500	
Tensile Strength at Break (psi)	MD	4900	D 882
	TD	3600	
1% Secant Modulus (psi)	MD	32000	D 638
	TD	36000	

Additives: No Slip, No Antiblock

LL4F 802 can - in principle - be used in food contact applications in the USA (FDA) and in Canada (HBP). Migration or use limitations may apply.

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility.



MARCO POLO
INTERNATIONAL, INC.
Worldwide Distributors of Plastic Resins

532 Broadhollow Road Suite 135 Melville, NY 11747 Tel: 631-629-4520 Fax: 631-629-4519