



MARPOL
LL4M 820-G
Linear Low Density Polyethylene



PRODUCT DATA SHEET

PROPERTY	VALUE	ASTM
Melt Index (g/10min)	20	D 1238
Density (g/cm ³)	0.925	
Tensile Strength at Break (psi)	1080	D 638
Tensile Strength at Yield (psi)	2100	D 638
Elongation at Break (%)	57	D 638
Flex Modulus 1% Secant (psi)	62400	D 790
Hardness, Shore D	50	D 2240
Notched Izod Impact (ft-lb/in)	10	D 256

Additives: No Slip, No Antiblock

Forms: Granules

Description: MARPOL® LL4M 820-G is a LLDPE resin designed for blending and good processability.

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility.

