



MARPOL PVC PIPE GRADE

Polyvinyl Chloride



PRODUCT DATA SHEET

PROPERTY	VALUE	ASTM
K-value (0.5 gm/100ml Cyclohexanone)	65	
Inherent Viscosity	0.89	D 5225
Relative Viscosity	2.17	D 1709A
Bulk Density (g/cc)	0.56	D 1895
Volatiles (% Maximum)	0.30	
Particle Size Through 40 Mesh (% Minimum)	99.0	D 1921
Particle Size Through 200 Mesh (% Minimum)	4.0	D 1921

ASTM Cell Classification: GP3-16040

Suggested Applications: PVC resin is typically used in rigid PVC compounds which can be processed through both single and multi-screw extrusion of pipe and conduit.

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility.



MARCO POLO
INTERNATIONAL, INC.
Worldwide Distributors of Plastic Resins

532 Broadhollow Road Suite 135 Melville, NY 11747 Tel: 631-629-4520 Fax: 631-629-4519